

Hydrogen on Graphene: an STM study

Stefan Heun

NEST, Istituto Nanoscienze – CNR and Scuola Normale Superiore, Piazza San Silvestro 12, 56127 Pisa, Italy

The realization of innovative hydrogen storage materials has worldwide strategic importance. In this context, graphene has recently attracted attention as a promising hydrogen storage medium. Indeed, graphene is lightweight, chemically stable, and exhibits attractive physico-chemical properties for hydrogen adsorption. Furthermore, the interaction between hydrogen and graphene can be controlled by chemical functionalization. However, experimental demonstrations of graphene-based hydrogen storage devices have yet to be reported.

The energetics of the chemisorption of hydrogen on graphene can be modified by the local curvature of the graphene sheet [1]. Based on scanning tunneling microscopy (STM) techniques, we report on site-selective adsorption of atomic hydrogen on convexly warped regions of monolayer graphene grown on SiC(0001). This system exhibits an intrinsic curvature owing to the interaction with the substrate [2]. We show that at low coverage hydrogen is found on convex areas of the graphene lattice [3]. No hydrogen is detected on concave regions. These findings are in agreement with theoretical models which suggest that both binding energy and adsorption barrier can be tuned by controlling the local curvature of the graphene lattice [1]. This curvature-dependence combined with the known graphene flexibility may be exploited for storage and controlled release of hydrogen at room temperature.

Theoretical studies regarding metal atoms (e.g. Ti) deposited on graphene suggest that such materials can adsorb up to 8 wt% gravimetric density of hydrogen. We investigated the deposition of titanium on graphene and its potential for hydrogen storage [4]. The titanium atoms form small islands (diameter ~10 nm). The Ti-covered graphene was exposed to molecular hydrogen (5 min at 1×10^{-7} mbar deuterium). The sample temperature was then increased up to 550°C with a constant heating rate of 10 K/s while measuring the mass-sensitive desorption. The desorption spectra show two peaks at 210°C and 290°C. Their intensity increases with increasing Ti coverage. Our data demonstrate the stability of hydrogen binding at room temperature and show that the hydrogen desorbs at moderate temperatures – both ideally matching technical requirements for hydrogen storage.

References:

- [1] V. Tozzini and V. Pellegrini, J. Phys. Chem. C 115 (2011) 25523.
- [2] S. Goler, C. Coletti, V. Piazza, P. Pingue, F. Colangelo, V. Pellegrini, K. V. Emtsev, S. Forti, U. Starke, F. Beltram, and S. Heun, Carbon 51 (2013) 249.
- [3] S. Goler, C. Coletti, V. Tozzini, V. Piazza, T. Mashoff, F. Beltram, V. Pellegrini, and S. Heun: Influence of graphene curvature on hydrogen adsorption: toward hydrogen storage devices, J. Phys. Chem. C 117 (2013) 11506.
- [4] T. Mashoff, M. Takamura, S. Tanabe, H. Hibino, F. Beltram, and S. Heun: Hydrogen storage with titanium-functionalized graphene, Appl. Phys. Lett. 103 (2013) 013903.