

Materials.it
2018**Bologna - Area della Ricerca CNR - Centro congressi**
October 22 - 26, 2018

Conference Chairs:

Corrado Spinella (Dipartimento di Scienze Fisiche e Tecnologie della Materia - CNR)

Maurizio Peruzzini (Dipartimento di Scienze Chimiche e Tecnologie dei Materiali - CNR)

Materials2018 - Submission - View**Abstract's title:** Optimization of few-layer black phosphorus for low-temperature magneto-transport studies**Submitting author:** Stefan Heun**Affiliation:** NEST, Istituto Nanoscienze-CNR and Scuola Normale Superiore**Affiliation Address:** Piazza San Silvestro 12, 56127 Pisa**Country:** Italy**Oral presentation/Poster (Author's request):** Oral presentation**Other authors and affiliations:**

Abstract

I will review our activities on black phosphorus (bP). We obtain high-quality few-layer bP flakes via mechanical exfoliation in nitrogen atmosphere, liquid phase exfoliation [1], and direct exfoliation in a polymer matrix which also protects the bP flakes at the same time [2].

The bP flakes are structurally characterized by AFM, Raman, and STM. I will present a study of surface modification on exfoliated bP flakes upon subsequent annealing steps, up to 550°C, well above the sublimation temperature. In particular, our attention is focused on the temperature range around 375°C - 400°C, when sublimation starts, and a controlled desorption from the surface occurs with the formation of characteristic well-aligned craters. With atomically-resolved STM images we show that the long axis of the craters is aligned along the [100] (zig-zag) direction of bP [3].

Flakes were also processed into Hall-bar devices. Low-temperature magneto-transport has shown clear evidence for weak localization in these flakes, with a strong in-plane anisotropy due to the crystalline anisotropy of bP [4]. A similar anisotropy was observed for high-field in-plane magnetic fields [5]. Furthermore, the nanocomposite bP/PMMA described above was used to directly fabricate bP devices from it, using the PMMA as an electron beam resist [6].

The author thanks the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (Grant Agreement No. 670173) for funding the project PHOSFUN "Phosphorene functionalization: a new platform for advanced multifunctional materials" through an ERC Advanced Grant.

[1] M. Serrano-Ruiz, M. Caporali, A. Ienco, V. Piazza, S. Heun, and M. Peruzzini, *Adv. Mater. Interfaces* **3** (2016) 1500441.

[2] Elisa Passaglia, Francesca Cicogna, Federica Costantino, Serena Coiai, Stefano Legnaioli, Giulia Lorenzetti, Silvia Borsacchi, Marco Geppi, Francesca Telesio, Stefan Heun, Andrea Ienco, Manuel Serrano Ruiz, and Maurizio Peruzzini, *Chem. Mater.***30** (2018) 2036.

[3] A. Kumar *et al.*, unpublished.

[4] N. Hemsworth, V. Tayari, F. Telesio, S. Xiang, S. Roddaro, M. Caporali, A. Ienco, M. Serrano-Ruiz, M. Peruzzini, G. Gervais, T. Szkopek, and S. Heun, *Phys. Rev. B* **94** (2016) 245404.

[5] F. Telesio *et al.*, unpublished.

[6] Francesca Telesio, Elisa Passaglia, Francesca Cicogna, Federica Costantino, Manuel Serrano-Ruiz, Maurizio Peruzzini, and Stefan Heun, *Nanotechnology* **29** (2018) 295601.