

Hydrogen Storage on Graphene

Stefan Heun

*NEST, Istituto Nanoscienze-CNR and Scuola Normale Superiore
Pisa, Italy*



National Enterprise for nanoScience and nanoTechnology

NEST

NEST Pisa



- **CNR:** Vittorio Pellegrini, Valentina Tozzini, Stefan Heun
- **IIT:** Camilla Coletti, Vincenzo Piazza, Sarah Goler, Torge Mashoff
- **SNS:** Massimo Morandini, Pasquale Pingue, Fabio Beltram

Outline

- Introduction to Hydrogen Storage
- Epitaxial Graphene
- Hydrogen Storage by Corrugation
- Hydrogen Storage by Functionalization

Outline


- Introduction to Hydrogen Storage
- Epitaxial Graphene
- Hydrogen Storage by Corrugation
- Hydrogen Storage by Functionalization

Hydrogen & energy

As a **fuel**, hydrogen has advantages:

- high energy-to-mass ratio
- $\text{H}_2 + 1/2 \text{O}_2 \rightarrow \text{H}_2\text{O} \quad \Delta H = -2.96\text{eV}$
- Non-toxic and “clean” (product = water)
- renewable

However, hydrogen is NOT an **energy source**: it must be produced e.g. by electrolysis, needing +2.96 eV, with zero balance with respect to energy production.










Hydrogen fuel cell

Hydrogen-fuelled vehicles



Hydrogen Storage

						
Liquid hydrogen	Cryo-adsorption	Interstitial metal hydride	Compressed hydrogen	Aluminate	Salt-like metal hydride	Water
LH2	Activated carbon	Laves Phase Comp./ FeTiH _x / LaNi ₅ H _x	CGH2	NaAlH ₄	MgH ₂	H ₂ O
100 mat.wt%	6.5 mat.wt%	2 mat.wt%	100 mat.wt%	5.5 mat.wt%	7.5 mat.wt%	11 mat.wt%
Operating temperature						
-253°C	> -200°C	0 - 30°C	25°C	70 - 170°C	330°C	>> 1000°C

Targets for **transport applications** not reached yet:

$$\rho_m > 5.5 \text{ wt\%}$$

$$\rho_v > 50 \text{ kg H}_2 / \text{m}^3$$

$$P_{eq} \approx 1 \text{ bar at } T < 100^\circ\text{C}$$

Compressed H₂:

High pressure and heavy container to support such pressure

Solid State:


Physisorption
Chemisorption

Liquid H₂:

Liquefaction needs energy and consumes more than 20% of the recoverable energy

Graphene for hydrogen storage

- Graphene is lightweight, inexpensive, robust, chemically stable
- Large surface area ($\sim 2600 \text{ m}^2/\text{g}$)
- Functionalized graphene has been predicted to adsorb up to 9 wt% of hydrogen




Yang et al., PRB 79 (2009) 075431

H storage in graphene

❖ Atomic hydrogen chemisorption has a small or negligible chemisorption barrier \Rightarrow feasible but H_2 must be cracked

❖ Physisorption weakly binds hydrogen \Rightarrow acceptable storage densities only at low temperatures and/or high pressure



❖ Molecular hydrogen chemi(de)sorption has high barrier (theoretical estimate $\sim eV$) \Rightarrow chemisorbed H is stable for transportation etc, but catalytic mechanisms are necessary in the loading-release phases


Outline

- Presentation of NEST
- Introduction to Hydrogen Storage
- Epitaxial Graphene
- Hydrogen Storage by Corrugation
- Hydrogen Storage by Functionalization

What is Graphene?




A **SINGLE** layer of carbon atoms!

The atoms are arranged in a honeycomb lattice composed of two intertwined equivalent sublattices.






Graphene growth on SiC

Graphene or thin graphite films form on SiC surfaces upon annealing at high temperatures as a result of SiC decomposition.




Bilayer of Si-C tetrahedra



Graphene:
Ordered stacking
Si(0001) face → Good thickness control



Graphene:
Rotational disorder
C(000 $\bar{1}$) face → Poor thickness control

Graphene growth on SiC(0001)




Buffer Layer

Topologically identical atomic carbon structure as graphene. Does not have the electronic band structure of graphene due to periodic sp^3 C-Si bonds.



F. Varchon, et al., PRB 77, 235412 (2008).

Theoretical Calculations



F. Varchon, et al., PRB 77, 235412 (2008).

Superstructure of both the buffer layer and monolayer graphene on the Si face from the periodic interaction with the substrate.

Buffer Layer







FIG. 2. (Color online) Total charge density of the buffer layer on SiC(001). (a) total charge density in the $6R3$ -SiC unit cell. (b) cross section of the total charge density along the line defined in (a). The black dots that appear when the cross section goes through the middle of an atom are due to the use of pseudopotentials (no core electrons).

F. Varchon, et al., PRB 77, 235412 (2008).



Monolayer Graphene




STM




$6\sqrt{3} \times 6\sqrt{3}$ -Superstructure



ML: Micro-Raman



Spectrum from 12um x 12um area
SiC background subtracted




Integrated intensity of 2D peak
Bright = ML graphene

Outline

- Presentation of NEST
- Introduction to Hydrogen Storage
- Epitaxial Graphene
- Hydrogen Storage by Corrugation
- Hydrogen Storage by Functionalization


Graphene Curvature

- Exploit graphene curvature for hydrogen storage at room temperature and pressure




Graphene Curvature

- Exploit graphene curvature for hydrogen storage at room temperature and pressure
- The hydrogen binding energy on graphene is strongly dependent on local curvature and it is larger on convex parts




Graphene Curvature

- Exploit graphene curvature for hydrogen storage at room temperature and pressure
- The hydrogen binding energy on graphene is strongly dependent on local curvature and it is larger on convex parts
- Atomic hydrogen spontaneously sticks on convex parts; inverting curvature H is expelled



H-dimers and tetramers





Para-dimer


Ortho-dimer

Tetramer


H adsorption and desorption



RMS roughness



DFT calculations



Outline

- Presentation of NEST
- Introduction to Hydrogen Storage
- Hydrogen Storage by Corrugation
- Hydrogen Storage by Functionalization


In collaboration with M. Takamura, S. Tanabe, H. Hibino

 **NTT** Basic Research Laboratories, Atsugi, Japan


 **RIKEN** Basic Research Laboratories, Atsugi, Japan
National Enterprise for nanoScience and nanoTechnology

Functionalized Graphene

- Functionalized graphene has been predicted to adsorb up to 9 wt% of hydrogen
- Modify graphene with various chemical species, such as calcium or transition metals (Titanium)




Lee et al., Nano Lett. 10 (2010) 793




Durgen et al., PRB 77 (2007) 085405

Titanium on graphene




ML graphene on SiC(0001)
with reconstruction




After deposition of Ti at RT


Titanium island growth




6% Coverage




16% Coverage




29% Coverage



53% Coverage



79% Coverage




100% Coverage

Thermal desorption spectroscopy



- Deposition of different amounts of Titanium
- Offering Hydrogen (D_2)
- (1×10^{-7} mbar for 5 min)
- Heating sample with constant rate (10K/s) up to $550^\circ C$
- Measuring mass-sensitive desorption with a mass spectrometer

Spectra for different Ti-coverages



TDS peak intensity

Peak fitting



All curves could be fitted nicely
with 2 peaks at 211C and 288 C

Conclusions

- Graphene is a promising material for hydrogen storage
- Curvature-dependent adsorption and desorption of hydrogen
 - reusable hydrogen storage devices that do not depend on temperature or pressure changes.
- Graphene functionalized by Ti:
 - Stability of hydrogen binding at room temperature
 - Hydrogen desorbes at moderate temperatures